

**Listing of Claims**

The following listing of claims replaces all prior versions and listings of claims in the application.

1. (Original): A film made from a polyester resin composition comprising 10 - 90 wt% of polyester (A) comprising ethylene terephthalate as a main constituent component and 90 - 10 wt% of crystalline polyester (B) different from said polyester (A), which film shows a half value width of recrystallization peak obtained by a differential scanning calorimeter (DSC) by lowering temperature of not more than 0.25.

2. (Original): The polyester film of claim 1, wherein the polyester resin composition comprises 10 - 70 wt% of polyester (A) comprising ethylene terephthalate as a main constituent component and 90 - 30 wt% of crystalline polyester (B), and the crystalline polyester (B) is a polyester selected from polybutylene terephthalate (PBT), polytrimethylene terephthalate (PTT) and polyethylene-2,6-naphthalate (PEN).

3. (Currently amended): The polyester film of claim 1 [[or 2]], wherein a peak temperature (Tc2) of the recrystallization peak is not less than 180°C.

4. (Currently amended): The polyester film of ~~any of claims 1—3~~ claim 1, wherein the polyester film has a reduced viscosity of not less than 0.80.

Preliminary Amendment  
Attorney Docket No. 042564

5. (Currently amended): The polyester film of ~~any of claims 1—4~~ claim 1, which is used for laminating on a metal sheet.

6. (Currently amended): The polyester film of ~~any of claims 1—4~~ claim 1, which is used for form processing.